

Ref #	Hits	Search Query	DBs	Default Operator	Plurals	Time Stamp
L1	28	(phosphor with (panel or film or sheet or shell)) and (phosphor with thickness) and ((support or substrate) near5 (carbon adj fiber))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/01/26 22:07
L2	18	(phosphor with (panel or film or sheet or shell)) and (phosphor with thickness) and ((support or substrate) near5 (carbon adj fiber)) and 250/484.4	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/01/26 22:06
L3	502	250/484.4	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/01/26 22:06
L4	351	427/69	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/01/26 22:06
L5	0	427/69 and (phosphor with (panel or film or sheet or shell)) and (phosphor with thickness) and ((support or substrate) near5 (carbon adj fiber))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/01/26 22:07
L6	74	427/69 and (phosphor with (panel or film or sheet or shell))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/01/26 22:07
L7	4	427/69 and (phosphor with (panel or film or sheet or shell)) and polyimide	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/01/26 22:07
L15	0	(thermal with conductivity)and (phosphor with (panel or film or sheet or shell)) with ((support or substrate) with (carbon adj fiber)). cfm.	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/01/26 22:17
L16	1	(conductivity) and (phosphor with (panel or film or sheet or shell)) with ((support or substrate) with (carbon adj fiber)).cfm.	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/01/26 22:17
L17	1	250/484.4 and (conductivity) and (phosphor with (panel or film or sheet or shell)) with ((support or substrate) with (carbon adj fiber)). cfm.	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/01/26 22:18